Generative Resin GR-19 OA

Instructions



pro3dure medical GmbH

Am Burgberg 13 D - 58642 Iserlohn Tel. +49 (0)2374 920050-0 Fax +49 (0)2374 920050-50 info@pro3dure.com www.pro3dure.com

Product description: photopolymerizable resin for 3D-printing systems (SLA, DLP) with irradiation sources ($\lambda \leq 405 \text{ nm}$) for orthodontic appliances



- Colour: clear and rose transparent, light blue
- Density: ca. 1.1 g/ml
- Viscosity: ca. 0,7 Pa s
- Green flex modulus: Elastic modulus: ca. 600 MPa Flexual strength: ca. 50 MPa Elongation at break: ca. 20 %
- Post cured material: (depends on postcuring unit) Elastic modulus: ca. 1700 MPa Flexual strength: ca. 90 MPa Elongation at break: ca. 10 % Hardness: ca. 80 Shore D

Storage:



Ordering information:


Standard packing:


1 kg bottle, clear transparent item no.: D1001493

1 kg bottle, rose transparent item no.: D1001492

1 kg bottle, light blue-transparent item no.: D1001491

These data result from measurements of a representative sample, which were determined within the scope of our quality assurance.





1. Product description

pro3dure's generative resin **GR-19 OA** is a resin for for 3D-printing systems (SLA, DLP) with irradiation sources ($\lambda \le 405$ nm) for orthodontic appliances. The formulation of GR-19 OA is optimized for the requirements of a robust production guaranteeing constant high quality. The GR-19 OA is successfully tested for biocompatibility, certainly meets all mechanical and application demands. The material can be used for build processes with layer thicknesses from 25 up to 100 µm. It is recommended to use the pro3dure medical curing device CD-1 or CD-2 for post curing.

2. Processing

- GR-19 OA bottles should be well shaked before use (fig 1).
- Make sure that GR-19 OA material is temperature adjusted up to 23 °C to 30 °C.
- Carefully pour GR-19 OA into the vat of the image projection unit (fig 2).
- Bubbles can be removed with a cleaned spatula or by a recoater routine.
- If it is possible, always store a bottle GR-19 OA in your production unit in order to avoid temperature differences during refilling.
- For the build parameter adjustment please refer to the machine data sheet.
- After the build process is finished a direct post treatment is recommended. If this cannot be guaranteed leave the produced objects in the liquid GR-19 OA resin.
- After cleaning of the parts with isopropanole \geq 97 % (approx. 3–5 min. in an ultrasonic bath) the objects are postcured in an adequate light curing unit (e.g. pro3dure's CD-1 or CD-2 for a period of 3-4 min.) in a protective gas atmosphere.
- The dental objects generated out of the generative resin GR-19 OA can be coated and repaired as usual.
- Impurity due to operation mistakes cannot be excluded. With respect to the low viscosity of the resin it is possible to filtrate the GR-19 OA. It is recommended to filtrate and stir up the resin on a regular base (fig 3). To avoid bubbles let **GR-19 OA** rest for 1 hour before usage.

Contains: Alkoxilated bisphenole-A-dimethacrylate, initiators, dyes and stabilisers.

3. Important

- To avoid detrimental effects on material quality do not expose the liquid material to irradiation under any circumstances.
- Deviations from the described manufacturing process may lead to different mechanical and optical properties of the GR-19 OA material.
- Ensure personal protective gear during processing.
- Caution: Polymerised resins are chemically resistant avoid stains on clothing!
- Avoid any contact with skin and eyes. In case of accidental contact, rinse with adequate running water, consulting a doctor if necessary.
- The lot number and the best before date are indicated on each GR-19 OA packaging. In case of claims please always indicate the lot number of the product. Do not use the product after expiry of the best before date.

Safety advice

pro3dure medical GmbH is not liable for any damages caused by improper application of the material. To be used by trained specialist personnel for the purpose indicated only.



